

DESCRIPTION

MXBON® 027452 is a non-CFC solvent based surface activator, which is designed to improve the speed of cure of MXBON® cyanoacrylate adhesives. The activator is HIGHLY FLAMMABLE. MXBON® 027452 can be pre- or post- applied to the bond. It is best used on post application on cyanoacrylate adhesives to ensure rapid fixturing.

PHYSICAL PROPERTIES

Liquid State	
Solvent Base	Acetone
Color	Clear to amber
Specific Gravity (20°C)	0.79
Flash Point (°C)	- 17 (Highly flammable)
On part life, minutes	1
Drying Time (20° C), seconds	< 30
Shelf life	24 months

DIRECTIONS FOR USE

- 1.Under no circumstances should the activator and the adhesive be mixed together. Use only in a well ventilated area.
- 2.Post Application: Apply MXBON® Cyanoacrylate adhesive on to the parts to be bonded.
- 3.Assemble parts to be bonded.
- 4.Apply MXBON® 027452 Activator over all exposed cyanoacrylate adhesive. Use approximately one drop of activator for every drop of exposed adhesive.

PRECAUTION

- 1. Activator must be handled in the applicable manner to highly flammable materials, and in compliance with local regulations. Do not store near oxidizing materials.
- 2. Acetone can affect some plastics and coatings. It is recommended that all surfaces be checked for compatibility before use.
- 3. The activator is light sensitive and the container should be stored in the dark when not in use.
- 4. Store in a cool (<25°C) dry location.

Note:

The data shown here is deemed reliable and is furnished for information only. Cartell Chemical Co. Ltd. cannot assume responsibility for the results obtained by others, over whose methods we have no control. It is the user's responsibility to determine the final suitability for their purpose, including the safe and proper handling of the product.

Cartell Chemical Co. Ltd specifically disclaims all warranties expressed or implied including warranties of salability or fitness of use, arising from the sale or use of Cartell Chemical Co. Ltd's products. Cartell Chemical Co. Ltd specifically disclaims any liability for damage of any kind including lost profits.

 Taiwan
 China

 +886-5-2203715
 +86-20-3921-8900





Thailand

+66-2-1706998