

### PRODUCT DESCRIPTION

MXBON® 017090 is designed to accelerate the cure process for MXBON® anaerobic products.

MXBON® 017090 offers the following characteristics:

<b>Chemistry</b>	Activator
<b>Appearance</b>	Transparent, blue-green liquid
<b>Base chemical</b>	Organic compound
<b>Solvent</b>	Dimethacrylate ester
<b>Viscosity</b>	Low
<b>Application</b>	Cure acceleration of MXBON® anaerobic products

### TYPICAL PROPERTIES

<b>Specific Gravity @ 25 °C</b>	1.02
<b>Viscosity @ 25 °C</b>	10~25 cPs
<b>Flash Point</b>	See SDS
<b>Fixture Time</b>	< 60 s

Fixture time and cure speed achieved depends on the adhesive used, bond gap and whether one to side has been activated:

- Fixture time ISO 4587, (seconds) two sides activation.
- Mild Steel (grit blasted) using MXBON® 31326 < 25 s

### GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be use with chlorine or other strong oxidizing materials. Where washing systems are used to clean the surfaces before bonding, it is important to check the compatibility of the washing solution with the adhesive. In some cases, these solutions can affect the cure and performance of the adhesive. This product is not recommended for use on certain plastics. Users are recommended to confirm compatibility of the product with such substrates.

Use always in a ventilated well area.

### Storage & Handling precaution

Keep activator in a cool and dry place. The storage temperature is recommended at 8 °C to 21 °C. For details, consult the Safety Data Sheet, (SDS).

1. Avoid contact with skin and eyes.
2. If contact with skin, rinse with water.
3. If adhesive gets into eye, keep eye open and rinse with water thoroughly. Seek medical attention immediately.
4. Keep the material out of children's reach.

### Directions for use

For assembly

1. Spray brush on the activator on both mating surfaces to be bonded. For small gaps, treatment of only one surface may be adequate. Contaminated surfaces may need repeated treatment or special degreasing prior to activation to remove any dissolvable contamination. Porous surfaces may have needed treatment with activator.
2. Allow the solvent time to evaporate under good ventilation until the surfaces are completely dry.
3. After activation, parts should be bonded within one month. Contamination of the surface before bonding should be prevented.
4. Apply the MXBON Anaerobic product to one or both surfaces and assemble parts immediately.
5. Where possible, move surfaces in relation to each other for a few seconds on assembly to properly distribute the adhesive and for maximum activation.
6. Secure the assembly and await fixturing before any further handling.

### Note

Informational purposes only and are believed to be reliable. However, Cartell Chemical Co., Ltd does not assume responsibility for any results obtained by persons over whose methods Cartell Chemical Co., Ltd has no control. It is the user's responsibility to determine the suitability of Cartell Chemical Co., Ltd's products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any Cartell Chemical Co., Ltd's products. Cartell Chemical Co., Ltd specifically disclaims all warranties express or implied, including warranties of merchantability or suitability for a particular purpose arising from sale or use of Cartell Chemical Co., Ltd's products. Cartell Chemical Co., Ltd further disclaims any liability for consequential or incremental damages of any kind including lost profits.