

北回化學股份有限公司為工業用接著劑、密封劑與特殊化學用品的專業製造商，為工業界提供了設計、製造、組裝與維修上最低成本、最優質可靠的解決方案。產品應用廣泛地橫跨傳統產業、電子產業、電機產業、醫療器材產業、鐵路運輸產業、船舶產業、運動器材產業、手工具與氣動工具、3C電子產品、汽機車等產業。

Cartell Chemical Co., Ltd., established in 1994, is a world-class manufacturer of industrial adhesives, sealants, and specialty chemical products. Its flagship brand MXBON® delivers high-performance, cost-effective, and reliable solutions for design, manufacturing, assembly, and maintenance across the industrial sector. MXBON® products are widely used in a broad range of industries, including traditional manufacturing, electronics, electrical engineering, medical equipment, railway transportation, shipbuilding, sports equipment, hand tools, pneumatic tools, 3C electronic products, and the automotive industry.

北回化學股份有限公司
Cartell Chemical Co., Ltd.

嘉義縣民雄工業區成功街18號
No.18 Cheng Gong Street,
Min-Shyong Industrial Park,
Chia-Yi Hsien, (621) Taiwan.
Tel: +886-5-2203715
Fax: +886-5-2203720
E-mail: sales@mxbon.com

更多資訊請掃



分公司/授權經銷商資訊
Branch/Authorized Dealer Information

※本型錄內容會有因產品改良而有變更的可能性，恕不另行通知。
Cartell Chemical Co., Ltd. 版權所有，翻印必究！ 2025.07



mxbon®



螺絲固定劑

THREAD LOCKERS



11222

低強度 具觸變性

Low strength, thixotropic

可用於M6或更小的螺絲固定與密封
為易拆卸型的螺絲固定劑
Lock and seal for M6 or smaller screws.
Removable.

11242

中強度 泛用型 具觸變性

Medium strength, general-purpose, thixotropic

可用於M20以下螺絲的固定與密封
適用於電鍍的不活性表面的材質
為可拆卸型的螺絲固定劑
Lock and seal for M20 or smaller screws.
Good for electroplating surface.
Removable.

11243

中強度 容油性 具觸變性

Medium strength, oil tolerance, thixotropic

可用於M20以下螺絲的固定與密封
適用輕油脂髒污表面，不鏽鋼及電鍍等不活性表面材質
為可拆卸型的螺絲固定劑
Lock and seal for M20 or smaller screws.
Suitable for lightly greased surfaces and passive substrates such as, stainless. steel & electroplating surface.
Removable.

11248

中強度 蠟狀固體

Medium strength, wax consistency

可用於M20以下螺絲的固定與密封
蠟狀半固體方便攜帶使用，且適用於輕油脂髒污表面，不鏽鋼及電鍍等不活性表面材質
為可拆卸型的螺絲固定劑
Lock and seal for M20 or smaller screws.
Semi solid stick form is incredibly convenient and portable, also suitable for lightly greased surfaces and passive substrates such as, stainless steel & electroplating surface.
Removable.

11262

高強度 高潤滑性 具觸變性

High strength, high lubricity, thixotropic

可用於M20以下螺絲的永久性固定與密封
在嚴苛的環境下，仍具有優良的防鏽及耐腐蝕特性
Lock and seal for M20 or smaller screws for permanent.
Excellent rust and corrosion resistance in harsh environments.

11263

高強度 耐化學性 快速固化 容油性

High strength, chemical resistant, fast curing, oil tolerance

可用於M25以下螺絲的固定與密封
適用於輕微油脂髒污表面、不鏽鋼及電鍍等不活性表面的材質
Lock and seal for M25 or smaller screws.
Suitable for lightly greased surfaces and passive substrates such as, stainless steel & electroplating surface.

11268

高強度 蠟狀固體

High strength, wax consistency

可用於M20以下螺絲的固定與密封
蠟狀半固體方便攜帶使用
適用於輕油脂髒污表面，不鏽鋼及電鍍等不活性表面材質
為可拆卸型的螺絲固定劑
Lock and seal for M20 or smaller screws.
Semi solid stick form is incredibly convenient and portable.
Suitable for lightly greased surfaces and passive substrates such as, stainless steel & electroplating surface.
Removable.

11271

高強度 低黏度 泛用型

High strength, low viscosity, general-purpose

可用於M25以下螺絲的永久性固定與密封
Lock and seal M25 or smaller screws for permanent assembly.

11272

高強度 具觸變性 耐高溫

High strength, thixotropic, heat resistance

耐高溫達230°C
可用於M36以下螺絲的永久性固定與密封
Heat resistance up to 230°C.
Lock and seal M36 or smaller screws for permanent assembly.

11277

高強度 高黏度

High strength, high viscosity

耐化學性特優，可防止螺絲生鏽及腐蝕
可用於M36以下螺絲的永久性固定與密封
Excellent chemical resistance, prevents rusting and corrosion of screws.
Lock and seal M36 or smaller screws for permanent assembly.

11290

中高強度 滲透型

Medium to high strength, penetration type

用於已裝配好的M2~M12螺絲固定與密封，也可用來密封焊道縫及鑄件的微孔
可防止螺絲生鏽及腐蝕
Lock and seal for M2~M12 screws after assembly, effective for sealing micro-pores on weld seams and castings.
Prevents rusting and corrosion of screws.

112701


高強度 鈍化表面專用

High strength, for passivated materials

抗熱性極佳
鈍化材質專用膠
可用於M20以下螺絲的固定與密封
Excellent heat resistance.
Specialized adhesive for Passivated Materials.
Lock & seal for M20 or smaller screws.

MXBON®螺絲固定劑，是單液厭氧固化型固定劑，能完全填補螺紋間隙，有效防止螺絲因震動、鬆脫、滲漏而導致的故障，取代傳統彈簧墊圈與雙螺母設計，大幅提升組裝穩固性與耐久性。使用時僅需將膠液塗於螺絲與內孔表面，即可快速固化；如需加速反應，可搭配MXBON促進劑使用。

MXBON® Threadlockers are anaerobic adhesives that cure in the absence of air and in the presence of metal ions. They effectively replace traditional mechanical locking methods such as spring washers, lock nuts, and split pins, simplifying product design and improving assembly reliability. They prevent loosening, vibration, and leakage, ensuring long-term fastening stability and reducing maintenance time. Simply apply the adhesive onto the screw and the internal thread surface. For faster results, use MXBON activator.



產品技術資料 Technical Information

型號 Item No.	外觀顏色 Appearance	螢光性 Fluorescence	黏度 Viscosity mPa.s (cP)	鬆脫扭矩 Breakaway N-m (lb-in)	摩擦扭矩 Prevail N-m (lb-in)	工作溫度 Working Temp. °C	固化時間 初固 Fixture Time	固化時間 全固 Fully Cured	認證 NSF
11222	紫色 Purple	◆	900—1,500 觸變性 Thixotropic	6 (52.8)	4 (35)	-54°C—150°C	15min	24hrs	◆
11242	藍色 Blue	◆	900—1,400 觸變性 Thixotropic	8—19 (70—167)	3—7 (26—62)	-54°C—150°C	5min	24hrs	◆
11243	藍色 Blue	◆	1,300—3,000 觸變性 Thixotropic	26 (229)	5 (44)	-54°C—180°C	10min	24hrs	◆
11248	藍色 Blue	◆	蠟狀 wax consistency	23 (204)	5 (43)	-54°C—150°C	5min	24hrs	
11262	紅色 Red	◆	1,200—2,400 觸變性 Thixotropic	26 (229)	32 (282)	-54°C—150°C	10min	24hrs	◆
11263	紅色 Red	◆	400—600	34 (299)	34 (299)	-54°C—180°C	10min	24hrs	◆
11268	紅色 Red	◆	蠟狀 wax consistency	10 (89)	4 (39)	-54°C—150°C	5min	24hrs	
11271	紅色 Red	◆	400—600	17—40 (150—352)	23—40 (202—352)	-54°C—150°C	10min	24hrs	◆
11272	紅色 Red		4,000—15,000 觸變性 Thixotropic	34 (299)	36 (317)	-54°C—230°C	30min	24hrs	◆
11277	紅色 Red	◆	6,000—8,000	32 (282)	32 (282)	-54°C—150°C	30min	24hrs	◆
11290	綠色 Green	◆	20—55	10 (88)	29 (255)	-54°C—150°C	20min	24hrs	◆
112701	綠色 Green	◆	500—900	26—50 (229—440)	≥15 (≥132)	-54°C—150°C	10min	24hrs	◆

*此列表之內容與數據皆以其產品技術資料表(TDS)為準，在決定選用接著劑之前，建議先進行實際測試以確保產品性能。
*The content and data within this list are based on the respective Technical Data Sheets (TDS) of each product. Before deciding on the adhesive to use, it is recommended to conduct actual tests to ensure product performance.

促進劑產品技術資料 Activator Technical Information

型號 Item No.	適用 Usage	特性 Property	主成分 Main Component	線上壽命 On-Part Life	乾燥時間 Dry Time	認證 NSF
017090	厭氧膠 厭氧型結構膠 For anaerobic adhesives, anaerobic structural adhesives	本款產品適用搭配於MXBON厭氧膠及密封膠。 低氣味、不閃燃、無毒配方，可縮短固化時間。 Formulated for compatibility with MXBON anaerobic adhesives and sealants. Low odor, non-flammable, and non-toxic formulation. Significantly reduces curing time.	甲基丙烯酸酯 Polyethylene Glycol Dimethacrylate	1 hour	不會乾燥 Will not dry	
017649	厭氧膠 厭氧型結構膠 For anaerobic adhesives, anaerobic structural adhesives	適用於所有厭氧膠的加速固化，縮短固定時間，增加填縫能力。 可先塗或後噴。典型應用：非活性金屬表面、金屬電鍍表面。 Anaerobic Adhesive Activator is suitable for all anaerobic adhesives and shortening the fixture time. We can apply it first or spray it later. Typical applications: inactive or plating metal surfaces.	丙酮 Acetone 庚烷 Heptane	14 days	≤100 sec	◆